

LABORATORIO ITALIANO GOMMA - CERISIE S.r.l.

To

IVG COLBACHINI S.p.A.

Via Fossona, 77

Date, June 24st, 2016 342-F-(EN)/2016 TR n°

Ref.

Your Confirm dated 27.11.15

35030 CERVARESE S. CROCE (PD)

Received

16.05.2016

Start tests 311.05.2016

End tests 09.06.2016

Page 1 of 2

S E

E T P 0 R R

Subject:

SUITABILITY TO BE USED IN CONTACT WITH MILK, ACCORDING TO BFR - XXI RECCOMANDATION - CATEGORY 2, ON A SAMPLE OF RUBBER COMPOUND MARKED "IVG 113891" SUPPLIED AS VULCANIZED RUBBER SHEETS 2 mm thick

Migrations after contact of the rubber sheets with the Simulators for 24 hours at 40°C (Category 2)

			(Category 2)	Requirements
Si	mulator: Distilled water			
•	p-phenylenediamine	mg/l	Not detectable (≤0,01)	≤ 0,3
•	Zinc dibenzyl dithiocarbamate	mg/kg elastomero	Not detectable (≤0,01)	≤ 0,1
Simulator: Acetic acid 3% (m/v) in water				
•	p-phenylenediamine	mg/l	Not detectable (≤0,01)	≤ 0,3
•	Zinc dibenzyl dithiocarbamate	mg/kg elastomero	Not detectable (≤0,01)	≤ 0,1
Si	mulator: Ethanol 10% (v/v) i	n water		
•	p-phenylenediamine	mg/l	Not detectable (≤0,01)	≤ 0,3
•	Zinc dibenzyl dithiocarbamate	mg/kg elastomero	Not detectable (≤0,01)	$\leq 0,1$



LABORATORIO ITALIANO GOMMA - CERISIE S.r.l.

Date, June 24st, 2016

TR n° **342-F-(EN)/2016**

Page 2 of 2

TEST REPORT

On the basis of the test results, on the basis of the recipe provided by the Customer and together with the test results contained in the RP 456/2011 of September 2nd 2011, we certifies that the examined rubber compound marked "IVG 113891" is in compliance with the requirements of the Recommendation XXI Category 2 of BfR for the use in contact with foods, including milk.

The sampling has been carried out by the Customer.

The contained results refer only to the tested sample.

This report cannot be partially reproduced without the laboratory approval.

E. Badomer, Operator
Proboner Elen lue

F. Negroni, *Director*