

CONTENT

AIR & WATER

AIR CONDITION

BRAKE BREATHING

CHEMICAL

COOLANT

FUEL GAS

HYDRAULIC

MATERIAL HANDLING

OIL COOLING POWERSTEERING

WELDING & GAS

INDEX

PVC

## Codan 3012 Oil Hose



## Codan 3012 -

Long length antistatic oil hose for transfer and delivery of mineral oils, greases and petroleum based products up to a maximum aromatic content of 50%. The liner is electrically conductive:  $R < 10^6$ Ohm/m (ISO 8031:2009). The cover is isolating R> 10<sup>9</sup> Ohm/m.

**Type nr.** 3012

Application: Oil / Grease / Universal Standard Length: 50 metres Working Temperature: -25°C to 100°C

Inside: NBR Colour: Black Reinforcement: PVA Outside: NBR/PVC Colour: Black

Standards: Std. branding: -

Inside dia. (mm)	Outside dia. (mm)	Working Pressure BAR	Burst Pressure BAR	Bend Radius (mm)	Weight (g/m)	Product code
6,0	14,0	25	75	60	190	3012006000
8,0	16,0	25	75	80	220	3012008000
10,0	18,0	25	75	100	251	3012010000
13,0	21,0	25	75	120	352	3012013000
16,0	25,0	25	75	150	415	3012016000
19,0	29,0	25	75	180	593	3012019000
25,0	36,0	25	75	240	785	3012025000
32,0	44,0	20	60	320	1.130	3012032000
38,0	51,0	20	60	380	1.470	3012038000
50,0	65,0	20	60	500	2.190	3012050000

This hose specification sheet has been prepared with great care in order to provide you with all the information you need. Written advice must be obtained from Codan Rubber before using any hose with untested media or before using in applications not covered in the product data sheet. Codan Rubber recommends regular maintenance, care and inspection of hoses before use. Hoses should be replaced if any physical damage is seen, especially to the cover of the hose or in the area around the couplings. All products must be stored in accordance with ISO 2230:2002 (Storage of vulcanised Rubber Products).

The individual conditions of an application will affect the life time of each product. Therefore please ensure that resistance to chemicals and cleaning procedures in our written product information is complied with. Codan Rubber's warranty is void in the event of misuse such as excessive bending, crushing, stretching, use

Please contact Codan Rubber for individual product manufacturing tolerances.

